



TEST LABORATORY

15708 Pomerado Road, Suite N208, Poway, CA 92064
Phone (858) 451-8868 – Fax (858) 451-9268
E-mail: sfi@sfifoundation.com

SFI Spec 3.2A Test R & D

Company Name: Heliotextil.SA Report Number: 19-347-1
Address: Rua dos Combatentes do Ultramar PO box 467 Date of Report: 08/01/19
City, State, Zip: 3701-914 S João da Madeira Purchase Order No.: VAT 500133263
Contact: Anabela Guimarães Phone: 00351256201100

Type of Test: **Flammability**
Part Number/Name: **Heat Press Ford Logo No.062**
50% Aramid / 50% Viscose 250g/m2 ± 5%
Specification/Revision: SFI Spec 3.2A Driver Suits/Effective: March 27, 2013
Test Procedure: Paragraph 5.1.1
Date of Test: 07/25/19

Requirements:

The average after flame time shall be 2.0 seconds or less. The average char length shall be six (6) inches or less. Any melting or dripping of the material is cause for failure.

Results:

| Sample | After Flame Time (Sec.) | Char Length (Inches) |
|----------------|----------------------------|-------------------------|
| 1 | 0.6 | 0.4 |
| 2 | 0.5 | 0.5 |
| 3 | 0.6 | 0.5 |
| 4 | 0.4 | 0.4 |
| 5 | 0.4 | 0.4 |
| Average | 0.5 | 0.44 |

This report applies only to the actual samples tested. SFI Laboratory does not certify, warrant or guarantee any products manufactured by others. Samples discarded within 1 year unless otherwise requested in writing by manufacturer.

SFI LABORATORY

A handwritten signature in black ink, appearing to read 'Michael J. Sherbo', is written over a horizontal line.

Michael J. Sherbo
Laboratory Manager